



Balanced Carbon Fabric

WOVEN FABRIC DATA SHEET

G. Angeloni reference

DYF 15 - 160 T

CHARACTERISTICS	
Mass per unit area	gr/sqm.
Weave	
Standard Width	mm.
Laminate thickness	mm.
Other informations	

Nominal	Tolerance	Normative
160	± 5%	ISO 4605
2 X 2 Twill		ISO 2113
1000	± 2,5%	
0,16	± 2,5%	(**)
Dyanotex flat fabric		

Nominal Construction	
Fibre description	
Carbon fiber producer	
Thread Count	ends/cm.
Weight distribution	gr/sqm.
	%

WARP		WEFT	
Dyanotex 15 mm TR 50S 15K - 1000 tex		Dyanotex 15 mm TR 50S 15K - 1000 tex	
GRAFIL		GRAFIL	
0,66	ISO 4602	0,66	ISO 4602
15k carbon fibre :	80 50%	15k carbon fibre :	80 50%

Selvages

weaving style :	LENO	Type :	thermofix glass 1670 dtex
-----------------	------	--------	---------------------------

Mechanical Properties of fiber	
Grafil TR50S	15K

Strength		Modulus	
4900	Mpa	240	Gpa

(**) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.

Date of Issue	18/10/2009	No. of Pages	1
---------------	------------	--------------	---

Note : Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

G. Angeloni srl

via Abate Tommaso , 72/A5 - 30020 Quarto d'Altino (VE) - ITALY

Tel. +39 0422 823801 - 780580 Fax +39 0422 782782

E-Mail : info@g-angeloni.com